

SBS – GP 3000

TECHNICAL DATA SHEET / SALES SPECIFICATION

Styrene - Butadiene block copolymer specially designed for asphalt modification, compounding and for solvent based adhesive applications.

TYPICAL POLYMER COMPOSITION

Molecular Structure	Linear
Styrene Content	30% By weight
Butadiene Content	70% By weight
Physical Form	Powder

SPECIFICATION

<u>Polymer Properties</u>	<u>Unit Measure</u>	<u>Typical Value</u>	<u>Range</u>	<u>Referred Standard</u>
Volatile Matter	%	0.2	1.0 max	ASTM D 5668
Ash Content	%	4	5 max	ASTM D 5667
Bound Styrene	%	30	29 – 32	-
Coupling Efficiency	%	90	85 min	ASTM D 5296
Molecular Weight (1000's)	Daltons	120	110 – 140	ASTM D 5296

The information and data presented herein are, to the best of our knowledge, true and accurate. They are intended for use by persons having technical skill and at their own discretion and risk; no warranty or guarantee, expressed or implied, is made and no liability is assumed in connection with any use of such information and data. Nothing herein shall be construed as a recommendation to infringe any existing patents or violate any applicable laws.